

technical data sheet.



leakfree.pro

waterproof & heatproof.





burned at \pm 900°C and cools after 15 seconds. SRI 104.36















leakfree.pro

description.

leakfree.^{pro} is a simple and economic waterproofing solution to protect walls against leakages, cracks, moldings, etc. Leakfree pro contains heat proofing properties with the highest solar reflectance index of 104.36 that reduces internal temperature of buildings considerably.

It is a one component, low viscosity polyurethane, water based fluid that cures to produce a highly elastic liquid membrane with strong adhesion to many types of surfaces with the help of primer.

It is based on aliphatic polyurethane with special inorganic fillers, which results in excellent mechanical, chemical, thermal, UV and natural element resistant properties.

recomended for.

Waterproofing and protection of:

- · exposed concrete slabs,
- walls,
- roofs,
- · bathrooms.
- · light roofs made of metal or fibrous cement.

limitation.

Not recommended for:

- unsound substrates,
- swimming pool surfaces in contact with chemically treated water,
- · ground water tank,
- indoor use.

features & benefits.

- · no thinning is required.
- excellent weather and UV resistance when used with topcoat. The white colour reflects solar energy (SRI 104.36) and so reduces the internal temperature of buildings considerably.

- excellent thermal resistance, product never turns soft. Max service temperature 80°C.
- · excellent mechanical properties.
- · Non-toxic after full cure.
- Water vapor transmission: The film breathes so there is no accumulation of humidity under the coat.

application prerequisties.

standard concrete substrate conditions:

Hardness: R₂₈ = 15Mpa.
Humidity: W < 10%.
Temperature: 5-35 °C.
Relative humidity: < 85%.

Primer selection for special conditions and substrates: **reflecto primer.**

application procedure.

Clean surface using a high pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, and cured membranes must be removed. Fill surface irregularities with the necessary product.

Priming:

Apply the required primer following the guidelines.

Mixina:

Use a low speed (300 rpm) mixer. Can optionally be thinned with 5% water for application by spraying (airless).

Application:

Apply the material with spray, roller or brush with at least 2-3 coats with 0.3 - 0.5 kg/m² per coat. Leave 2 to 4 hours between coats.

For spraying, it can be mixed with xylene with ratio 1:5.

For horizontal concrete slab, **topcoat.** Pro (UV protection, scratch resistance, self cleaning) is recommended. To improve service life, scratch resistance, cleaner surface, and antimold properties.

consumption.

Every coat: 0.3-0.5 kg/m² minimum 3 coat

Minimum total consumption: 1.0-1.5 kg/m².

For warranty leakfree application, the total consumption ought to be 1:1 (1kg/1m²)

Application on Walls:

The use of **reflecto primer** is recommended to extend service life, with a consumption of 0.1 kg/m².

Mix pail well before use. Minimum coats are 2-3, recommended with $0.3\text{-}0.5~\text{kg/m}^2$ per coat, or a total of 0.7-1 kg/m². Paint in cross perpendicular directions for every coat.

Application on Horizontal concrete slab:

Primer selection for different substrates is recommended. Depending on the substrates, usually consumption of **reflecto primer** consumption of 0.1-0.2 kg/m² for reflecto primer is sufficient.

Coat **leakfree.** Pro using roller, brush or spray method with a total consumption of 1 - 1.5 kg with a minimum of 3 layers. Paint in cross perpendicular directions for every coat with a consumption of 0.3 - 0.5 kg per m2 per layer.

cleaning.

Clean tools and equipment with water before paint dries.

packaging.

1kg, 4kg, 20kg

shelf life.

Can be kept for a maximum of 6 months in the original unopened pails in dry conditions with temperatures between 5-30°C. Once a pail has been opened, use it as soon as possible.

technical specifications.

The product in liquid form (before application):

property	unit	method	specification
Viscosity (BROOKFIELD)	сР	ASTM D2196-86, @ 25°C	1000-2000
Specific weight	gr/cm³	ASTM D1475 / DIN 53217 / ISO 2811,@ 20°C	1.1
Flash point	°C	ASTM D93, closed cup	N/A
Tack free time, @ 77 °F (25°C) & 55% RH	hours	-	4
Recoat time	hours	-	2 to 4

The cured membrane

property	unit	method	specification
Service temperature	°C	-	-20 to 80
Max. temperature short time (shock)	°C	-	200
Hardness	Shore A	ASTM D2240 / DIN 53505 / ISO R868	60





The cured membrane

property	unit	method	specification
Tensile strength at break @ 23 °C	Kg/cm² (N/mm²)	ASTM D412 / EN-ISO-527-3	55
Percent elongation @ 23 °C	%	ASTM D412 / EN-ISO-527-3	> 800
Water vapor transmission	gr/m².hr	ASTM E96 (Water Method)	0.8
Adhesion to concrete	Kg/cm² (N/mm²)	ASTM D4541	> 2
Solar Reflectivity Index ISO 9050:2003	-	ASTM C1371:2004a	SRI 104.36

classification according to EOTA (European Organization of Technical Assessment)

Certified quality, environmental and occupational health & safety management systems: ISO 9001/14001 & OHSAS 18001.

none of our published instructions and specifications, in writing or otherwise, are binding either in general or with respect to any third party rights, or do they relieve interested parties of their duty to subject the product to an adequate examination of its suitability. in no event will reflecto. be responsible for damages of any nature, whatsoever, resulting from the use of or reliance upon information or the product to which information refers.



